



**FERROCCSA**  
FERRO DE OCCIDENTE, S.A DE C.V.

## LAMINA ROLADO CALIENTE Y FRIO

ESPESOR			PESO EN KILOGRAMOS					
calibre	pulg.	m.m.	3' x 6'	3' x 8'	3' x 10'	4' x 8'	4' x 10'	kg/m2
3	0.2391	6.0731	76.699	106.265	132.832	141.687	177.109	47.660
4	0.2242	5.6947	74.732	99.643	124.554	132.858	166.072	44.690
5	0.2092	5.3137	69.732	92.977	116.221	123.969	154.961	41.700
6	0.1943	4.9352	64.766	86.354	107.934	115.139	143.924	38.730
7	0.1793	4.5542	59.766	79.688	99.610	106.251	132.813	35.740
8	0.1644	4.1758	54.799	73.066	91.332	97.421	121.776	32.770
9	0.1495	3.7973	49.833	66.444	83.055	88.591	110.739	29.800
10	0.1345	3.4163	44.833	59.777	74.721	79.703	99.628	26.810
1/8"	0.1250	3.1750	41.666	55.555	69.444	74.073	92.591	24.916
11	0.1196	3.0378	39.866	53.155	66.444	70.878	88.591	23.840
12	0.1046	2.6568	34.866	46.488	58.110	61.984	77.481	20.850
13	0.0897	2.2784	29.900	39.866	49.833	53.155	66.444	17.880
14	0.0747	1.8974	24.900	33.200	41.499	44.266	55.333	14.890
15	0.0673	1.7094	22.433	29.911	37.388	39.881	49.851	13.415
16	0.0598	1.5189	19.933	26.577	33.222	35.437	44.296	11.920
17	0.0538	1.3665	17.933	23.911	29.889	31.881	39.851	10.724
18	0.0478	1.2141	15.933	21.244	26.555	28.326	35.407	9.528
19	0.0418	1.0617	13.933	18.578	23.222	24.770	30.963	8.332
20	0.0359	0.9119	11.967	15.955	19.944	21.274	26.592	7.156
21	0.0329	0.8357	10.967	14.622	18.278	19.496	24.370	6.558
22	0.0299	0.7595	9.967	13.289	16.611	17.718	22.148	5.960
23	0.0269	0.6833	8.967	11.955	14.944	15.941	19.926	5.362
24	0.0239	0.6071	7.967	10.622	13.278	14.163	17.703	4.764
25	0.0209	0.5309	6.967	9.289	11.611	12.385	15.481	4.166
26	0.0179	0.4547	5.967	7.955	9.944	10.607	13.259	3.568
27	0.0164	0.4166	5.467	7.289	9.111	9.718	12.148	3.269
28	0.0149	0.3785	4.967	6.622	8.278	8.830	11.037	2.970
29	0.0135	0.3429	4.500	6.000	7.500	8.000	10.000	2.691
30	0.0120	0.3048	4.000	5.333	6.667	7.111	8.889	2.392